

Feature	HCR100
Apperence	Transparent, slightly yellowish crystallized bead
Density,Bulk (gr/dm ³ , 250C)	1,06 ± 0,01
Color (%50 toluen, Hazen)	Max. 50
Softening Point, (0C)	105 ± 3,0
Viscosity cps, 140 1600C	5000 ± 100 (1400C) 700 ± (1600C)
Glass to liquid transition 0C, Tg	Max.50
Molecular Weight	650 ± 50