

Feature	OPEW 1015	OPEW 1020
Apperence	White powder	Light yellow powder
Color	0,0 – 140,0	0,0 – 140,0
Density, bulk (gr/dm3, 200C)	500 ± 25	500 ± 25
Density Melted (gr/dm3,1200C)	930 ± 15	930 ± 15
Melting Point ( 0C)	100 ± 10	100 ± 10
Vicat Penetration Test (A* 0,1 mm, at 25 0C)	MAX. 5,0	MAX. 5,0
Acid Value (mgKOH/gr)	15 ± 1	19 ± 1
Viscosite cps, 1400C	50 ± 25	50 ± 25
Ash , % (at 750oC)	0,01-0,10	0,01-0,10
CMHC (< C 25)	Max. 5,0 %	Max. 5,0 %
Average molecular weight	1300 ± 200	1300 ± 200