

Feature	PARWAX 102	PARWAX 104
Apperence (250C)	White Slab	White Slab
Description	Light Paraffin Wax	Heavy Paraffin Wax
Oil Ratio (%)	1,0 – 3,0	3,0 – 5,0
Density (150C) Gr/cm3	0,75 ± 0,01	0,75 ± 0,01
Dropping Point (0C)	50,0 ± 2,0	50,0 ± 2,0
Melting Point (0C)	57,0 – 61,0	55,0 – 60,0
Viscosity Kinematic cst, 1000C	4,0 ± 1,0	5,0 ± 1,0
Vicat Penetration Test (A * 1,0 mm, at 25 0C)	25,0 ± 3,0	25,0 ± 3,0