

PACKAGING

20 / 25 kg. in PP sacks with PE lamination.

Feature	CaSt	ZnSt
Apperence	White powder	White Powder
Density (gr/dm ³ , 200C)	550 ± 50	1,0 ± 0,05
Melting Point (0C)	185 ± 5	123 ± 3
Humidity (1050C), %	0 - 2	Max. 1
Ash , % (300oC)	18 ± 1,0	21 ± 1,0